

PRIMACEM

Bonding bridge.



Tacking effect primer, indicated for the preparation of bonding bridges between new and old concrete and mortars supports.

Properties

- Can be applied with brush or microfiber roller in one hand
- Resistant to alkalis.
- Consolidant.
- High adhesion to different substrates.
- Low sensitivity to water.
- Water based, no flammable.
- Free from plasticizers, solvents, ammonia and free from emulsifiers.
- The product is supplied ready for use.

Amount needed

Performance over consolidated substrates and in good levelness conditions:
Primacem (1 coat) – 0,10 l/m²

Technical data

- Aqueous dispersion of copolymer
- Milky liquid
- Solids: 36,5 %
- PH between 8 y 9
- Temperature of application between 5°C to 35°C
- Dry to touch: permanent tack
- Minimum film forming temperature: 4°C
- Specific weight at 20°C: 1,04 g/ml
- Viscosity Brookfield RVT at 20°C (3/20 rpm): 1.700 – 2.200 mPa•s
- Emulsifying system: non-ionic
- Appearance of the film: high plasticity
- Re-coatable: up to 15 days after application
- Stability to frost: very good
- Stability to the outside: aliphatic
- Stability to traffic: null
- Adhesion: clean and dry porous surfaces
- Finish: colourless gloss
- Maximum thickness: 60 µm

Application

The surface must be dry, clean and firm, free of grease or oils. Primacem is applied by brush or microfibre roller in one coat.

- Before applying homogenize the product perfectly.
- Apply at temperatures between 5°C and 35°C.
- The surface must be free of dust, grease and moisture.
- Allow to dry until the product becomes translucent before applying the mortar.
- Never apply thicknesses of more than 1 cm of mortar.

Special precautions

If the product comes into contact with eyes, wash with plenty of water for 15 minutes. In the event of contact with skin, wash with soap and water. Do not ingest. If swallowed, do not induce vomiting and seek medical assistance immediately.

It is recommended to comply with the following measures:

- Good ventilation.
- Safety glasses.
- Rubber gloves.

Empty containers must be disposed of in accordance with current local regulations. To prevent the product from drying or thickening, close the lid after each use. This product is not toxic, dangerous or flammable under normal conditions of handling. It does not contain any harmful substances that under current regulations call for any additional measures in terms of its labelling. Keep out of the reach of children.

Packaging

It is available in container of 5 and 25 litres.

Cleaning of tools

Tools should be cleaned with water and soap immediately after use.

Storage conditions

The product should be stored in its closed original packaging, protected from weather conditions at temperatures between 10°C and 30°C in a dry and well ventilated place, away from direct heat and sunlight. Shelf life is 1 year from the date of production, if stored in well-preserved conditions.



The product should not be used for purposes other than those specified without first having instructions in writing. It is always the user's responsibility to take suitable measures in order to comply with the requirements established in local legislation. Product safety sheets are available for professionals. This technical data sheet will be valid until a new edition appears.

Last updated: June 2017