



TopSealer® WT

Topsealer® WT Pool

One-component water-based sealant for swimming pools.



Topsealer® WT Pool is a one-component water-based sealer for the Atlanttic system that creates a protective and consolidating film.

Topsealer® WT Pool is formulated on the basis of acrylic copolymers in emulsion, stable in humid environment.

Properties

- Improves mechanical and chemical resistance.
- Stable in humid environment.
- Resistant to the alkalinity of microcement.
- High adhesion
- Easy application
- Low water absorption.
- Water-based, non-flammable.
- Permeable to water vapour.

Perfomance

1 layer: 0.06 L/m² (0.06 l/m²)

Technical data

Type	Water based emulsion
Appearance	Milky liquid
Solids	14%
PH	Between 6.5 and 7.5
Viscosity (Ford Cup 4)	10 -11 seconds
Application temperature	From 5°C to 35°C
Touch-drying	20 minutes

(*)Depends on temperature and humidity.

Application

Before applying Topsealer® WT Pool it is essential to check that the substrate is dry and dust-free. Depending on the climatic conditions and the ventilation of the working space, it is necessary to allow at least 24 hours before applying the primer on the microcement.

Apply only one layer with a short pile microfibre roller

If the sealant is applied and it rains within 7 days, this will cause staining of the sealant. It must be dried, sanded and re-varnished.

Special precautions

It is essential to follow the instructions on the label of the container. For further information, please refer to the safety data sheet of the product. Empty containers must be disposed of in accordance with current legislation. To prevent the product from drying out, close the lid after each use.

Packaging

It comes in 5-litre containers.

Cleaning of tools

Tools should be washed with soap and water immediately after use.

Storage conditions

The product must be stored in its original closed container and protected from direct sunlight in the open air at temperatures between 10°C and 30°C, in a dry and well-ventilated place, in a dry and well-ventilated place ventilated, away from heat sources and direct sunlight. Time of use is 1 year from date of manufacture, properly stored.



The product must not be used for purposes other than those specified, without first having written instruction in its handling. It is always the responsibility of the user to take appropriate measures in order to comply with legislative requirements. The Safety Data Sheets of the product are available to the professional.

last edition: May 2024