



TopSealer®



TopSealer® WT All in One Ready to use Sealer

Topsealer® WT All in One by Topciment® is a one-component water-based polyurethane varnish developed for the protection of the ready to use microcement Efectto Quartz. It can also be used on epoxy microcement, parquet or wood.

Topsealer® WT All in One provides good mechanical and chemical resistance.

Available in matt or satin.

Characteristics

- Especially recommended for protecting ready to use microcement surfaces, Efectto Quartz.
- Good abrasion resistance.
- Good chemical resistance.
- Unalterable to ultraviolet light (no yellowing).
- Significantly enhances the colour of ready to use microcement coatings, maintaining the original texture.
- Quick drying and easy application.
- Apply 3 coats in one day, allowing 4 hours drying time between coats, or 4 coats in wet and high traffic areas.
- After 7 days it reaches its maximum capacity.

Preparation

Stir the contents before use, especially the matt varnish in order to homogenise the dispersion of the fillers.
No dilution required. Ready to use.

Uses and areas of application

Product for protection, sealing and as a decorative finish, formulated with aliphatic polyurethane resins with one-component water-based polycarbonate that give it extraordinary characteristics.

It is highly transparent and highly resistant to yellowing. Like all polyurethanes, it is highly resistant to wear, dirt and certain chemical products.

Ideal for application on our ready-to-use microcement system.

Do not apply under any circumstances on the two-component microcement systems Standard and Nature or on our one-component microcement Evolution.

Consumption

Consumption for Topsealer® All in One:

- 0,2 L/m² (for 3 coats)
- 0,25 L/m² (for 4 coats)

Technical data

- Colour: Transparent (in dry layer).
- Finish: Satin or mat
- Matte finish solids: 32,5 - 36%
- Satin finish solids: 25,5 - 28,5%
- Viscosity in Ford Cup 4mm: 35 ± 10s
- Application temperature: >8°C
- Dry to touch: (23°C, 50% wt): 1 - 2h
- Recoating: (23°C, 50% wt): 4h
- Drying (23°C, 50% wt): 24h
- Curing time: 7 days to achieve its maximum capacity

Characteristics

- Aliphatic polyurethane dispersion with polycarbonate
- Matte finish solids: 32,5 - 36%
- Satin finish solids: 25,5 - 28,5%

Preparation of the substrate

Before varnishing, the substrate must be properly prepared. It must be dry, clean and free of dust, grease or dirt. For a thorough cleaning use our detergent cleaner ECOCLEAN PRO.

If the surface has been previously varnished or painted, the previous coating must be removed, especially if it is damaged or deteriorated. This can be done by sanding or stripping, making sure to leave the surface in good condition.

If repair, consolidation or joint sealing is required, proceed before priming.

If the original coating is in good condition, a preliminary test of compatibility with the substrate can be carried out in an inconspicuous area.

Application

Before applying Topsealer® All in One, check that the microcement is dry and free of dust. Depending on the climatic conditions and the ventilation of the work area, it will be necessary to ensure correct drying of the ready-to-use microcement. It is recommended to allow at least 24/48 hours to elapse before applying the polyurethane on the microcement.

- Apply with a brush or short nap or microfibre velour roller.
- The application must be carried out at ambient temperatures between 10°C and 30°C.
- Apply 3-4 coats of varnish in one day, leaving 4 hours between coats.
We recommend lightly sanding the first and second coats with 400 grit sandpaper. In case of wet and/or high traffic areas, apply 4 coats of varnish.

Allow to dry for at least 7 days before use to achieve maximum performance. The total curing time will depend on the environmental conditions. At 23°C and 50% humidity it will take 7 days.

It seals the pore of the microcement against running water (occasional contact), but is not a waterproofing agent against watertight water (permanent contact). In the case of soap or detergent residues, rinse immediately, as these can cause marks or grooves to appear.

Chemical resistance one-component matte/satin

PRODUCT	7 DAYS AFTER VARNISH APPLICATION		
	1H	3H	8H
WATER	5	5	5
BLEACH	4	4	1
OIL	4	4	4
SALFUMÁN	4	3	3
8% VINEGAR	5	4	4
WINE	3	3	2
SOAP	5	5	3
BLEACH-FREE CLEANER	5	4	4

Special precautions

Non-flammable product.

In case of contact with skin wash with soap and water. Never use solvents or thinners. Do not swallow. In case of ingestion do not induce vomiting and seek medical attention immediately.

The following measures are recommended:

- Good ventilation.
- Use of mask with chemical absorbent.
- Protective goggles to prevent splashing.
- Rubber gloves.

Empty containers should be disposed of in accordance with current legislation. To prevent the product from drying out or thickening, close the lid after each use. Keep out of reach of children.

Packaging

It is available in 2 and 5 litre containers.

Cleaning of tools

The tools are washed with water immediately after use.

Storage conditions

It should be stored in its original closed container and protected from the weather at temperatures between 10°C and 30°C, in a dry and well ventilated place, away from heat sources and direct sunlight. The shelf life is 1 year from the date of manufacture, if stored properly.



The product must not be used for purposes other than those specified without first having written instruction in its handling. It is always the responsibility of the user to take appropriate to comply with the requirements of legislation. The Safety Data Sheets of the product are available to the professional.

Last edition: October 2023